

Technical information

# Polimal® 104 AWTP-2

DATE: 14.12.2021

**Polimal® 104 AWTP-2** is an accelerated, thixotropic, orthophthalic, unsaturated polyester resin with colorful curing indicator system.

This resin meets the requirements of **DIN 16 946/2 type 1140**.

## APPLICATION

**Polimal® 104 AWTP-2** is designed for the production of polyester glass laminates by hand lay-up or spray-up. Enables producing a laminate up to 5 mm thick

## PACKAGING

220 kg, 1100 kg

## SHELF LIFE

3 months from the production date.

## STORAGE

The resin should be stored in closed original containers, in dry, well ventilated and shaded warehouse compartments adapted for storage of combustible materials at a temperature below 25°C.

## CURING SYSTEM

Good curing conditions are received while using : 1-2% of hardener MEKP e.g. Luperox K-1S. The gel time control is reached by changing the amount of the hardener ( within the range as above). By reducing the amount of hardener [the best within the range of 10-20 ml/kg of the resin], the temperature peak can be decreased. It requires to increase the amount of accelerator in order to keep the gel time. Finally, curing could be optimized by post-curing at elevated temperatures.

## SPECIFICATION

| Parameter                                   | Unit  | Value          |
|---|-------|----------------|
| <b>Viscosity (25°C)</b><br>acc. ISO 3219    | mPa s | <b>250+350</b> |
| <b>Gel time (25°C)</b><br>acc. ISO 2535     | min   | <b>27+35</b>   |
| <b>Flexural strength</b><br>acc ISO 178     | MPa   | <b>min 120</b> |
| <b>Tensile strength</b><br>acc . ISO 527    | MPa   | <b>min 80</b>  |
| <b>Tensile modulus</b><br>acc . ISO 527     | MPa   | <b>3600</b>    |
| <b>Elongation at break</b><br>acc ISO 527   | %     | <b>min 3,0</b> |
| <b>Heat resistance, HDT</b><br>acc . ISO 75 | °C    | <b>min 90</b>  |
| <b>Barcol Hardness</b><br>acc . ASTM D 2583 | °B    | <b>&gt; 40</b> |
| <b>Absorbability of water after lays</b>    | mg    | <b>&lt; 60</b> |

**Curing system:** 2% MEKP medium active eg. Luperox K-1S

Mechanical parameters refer to unreinforced resin cured for 24 hours at room temperature and post-cured for 8 hours at 80 °C.

**Luperox®** is a trade name registered for products of **ARKEMA** company.

*The data and suggestions contained in this material are based on our own research and considered by us to be reliable. However, we cannot accept any liability for actions and losses resulting directly or indirectly from the use of the products. The user should check the quality, safety and features of the product before applying it. ATTENTION: This information does not replace the Safety Data Sheet or the Technical Sheet which are master documents available upon request.*

